



R.R.4, Eckville, AB T0M 0X0
 (403) 746-6060, Fax (403) 746-3330

SIZE AND SPECIFICATIONS

COILED ALUMINUM PIPE GRADE 6063 T1A AND 6063 T1B

OUTSIDE DIAMETER (MM)	WALL THICKNESS (MM)	AVERAGE LENGTH PER COIL (METERS)	6063 T1A M.O.P. (kPa)	6063 T1B M.O.P. (kPa)
48.3	2.2	2350	5247	6267
	2.8	2350	6678	7976*
60.3	2.2	1450	4080	4880
	2.8	1450	5349	6388
	3.2	1450	6113	7301*
	3.9	1450	7451	8899*
73.0	3.0	1000	4734	5654*
	3.9	1000	6155	7351*
82.6	3.6	800	5021	5997

NOTE:

1. M.O.P. is based on 80% of Yield Strength. This will allow testing at 25% above M.O.P.
2. Minimum material Yield Strength for 6063 T1A is 72 mPa, and 6063 T1B is 86 mPa.

* Please check the AVAILBILITY of 6063 T 1B.